



BLUE WATER[®] MARINE PAINT

- **Hard Modified Boosted Epoxy**
- **Full Season Protection Boosted with SCX™ - Slime Control Xtra**
- **Exceptional Durable Finish**
- **Ideal for Fiberglass, Wood, Steel**
- **Tremendous Protection for Extreme Fouling Conditions**

COPPER PRO™ SCX™ 67 HARD

SLIME CONTROL XTRA™

HIGH LOAD BOOSTED
MODIFIED EPOXY

PLATINUM PLUS SERIES

High Load Boosted Modified Epoxy-Platinum Plus Series

Copper Pro™ SCX™ 67 Hard provides full antifouling protection against barnacles, algae and hydroids in salt and fresh water on boat bottoms only. SCX™ - SLIME CONTROL XTRA™ - acts like a sunscreen to prevent slime and algae. Its modified epoxy base renders a smooth finish with durability and abrasion resistance. Copper Pro™ SCX™ 67 Hard releases biocide by the exposure of paint film to the water. Copper Pro™ SCX™ 67 Hard has universal application over all types of properly prepared bottom paints (except aluminum). For use on fast fiberglass boats, as well as wood and steel hulls, extended protection is possible, since performance is directly proportional to the amount of paint applied.

Surface Preparation: Surface must always be clean, dry and properly prepared prior to painting. Failure to do so will lead to eventually blistering and/or peeling. All sanded surfaces must be wiped clean with 973 Dewaxer to remove sanding residue.

General Application: For use on boats below the true waterline. Can be brushed or rolled on fiberglass, wood, steel and previously painted surfaces per application systems below. Do not use on aluminum. Apply at least 2 coats for best performance, as the life of the paint is proportional to the number of coats applied.

Mixing and Thinning: Shake or mix thoroughly and stir continuously while using. Thin when necessary with 974 Thinner.

Theoretical Coverage: Depending on surface conditions, one gallon of bottom paint will usually cover over 400 square feet of surface when brushed or rolled.

Clean Up: Use 974 Thinner for cleaning equipment and paint brushes.

Estimated Dry Times: Bottom paints are designed for overcoating after an overnight dry. Prior to launching, allow a minimum dry of overnight and a maximum dry time of 60 days. If drying conditions are poor, or if paint was applied too thickly, longer periods of drying will be required. Fresh coats of paint must be

thoroughly dry before overcoating.

Yearly Repainting: Scrub bottom clean at haul-out. Repaint only if old paint is sound and tight; if not, remove it by sanding or with paint remover. If old paint is rough, sand it with 100-150 grit sandpaper. Prepare seams, nicks and chips as below. Spotcoat any scuffs with antifoulant. Apply 2 coats of antifoulant.

On Bare Wood: If seams are not flush, fill them with seam compound. Dry several days until skin forms. Do not sand. Fill nicks with trowel cement, dry hard, sand, apply antifoulant (reduced 10%) then follow with 2 additional unreduced coats of antifoulant.

On Bare Fiberglass: Dewax by washing with 973 Dewaxer, remove dissolved wax at once with clean paper towels or rags; repeat; sand hard to a dull finish with 80-100 grit sandpaper. Fill any chips with trowel cement, dry hard, sand. Apply 3-5 coats of 8000A/8000B Bottom Protect High Build Epoxy Primer, then apply 2 coats of antifoulant.

On Bare Steel: Sandblast surface to a near white metal; remove blast residue with a broom and airhose. Wipe off with 973 Dewaxer. Do not sand. Fill in any imperfections with fairing compound. Sand smooth and wipe clean. Apply 3-5 coats of 8000A/8000B Bottom Protect High Build Epoxy Primer, then apply 2 coats of antifoulant.

ACTIVE INGREDIENTS:

CUPROUS OXIDE	67.00%
N-CYCLOPROPYL-N'-(1,1-DIMETHYL)	
-6-(METHYLTHIO) -1,3,5- TRIZINE-2, -4	1.96%
-DIAMINE	
INERT INGREDIENTS	31.04%
TOTAL:	100.00%
COPPER AS METALLIC =	59.50%

BLUE WATER MARINE PAINT

Distributed by

BoatZincs.com

EPA REG. 74681-4
EPA ESTABLISHMENT 74681-NJ-1
CONTAINS PETROLEUM DISTILLATE